



The product

Flexjoint expansion joint tapes are made of EPDM rubber and are the perfect solution for roof and structural waterproofing.

- highly elastic, absorbs 3D movements simultaneously
- durable without plasticisers
- durable connection without weak points due to vulcanisation technology
- low installation height
- flame-resistant carbon fleece bonds excellently without pre-treatment
- ideal for bitumen, liquid plastic and epoxy adhesives






Our assortment

Flexjoint EP20


+/- 20mm expandable in longitudinal/transverse/vertical direction diagonally up to +/- 35mm





Flexjoint EP40


+/- 40mm expandable in longitudinal/transverse/vertical direction diagonally up to +/- 70mm





Flexjoint EP75


 $+/-75\,\mathrm{mm}$ expandable in longitudinal/transverse/vertical direction diagonally up to $+/-130\,\mathrm{mm}$





Flexjoint EP100


+/- 100mm expandable in longitudinal/transverse/vertical direction diagonally up to +/- 175mm





Flexjoint EP125

+/- 125mm expandable in longitudinal/transverse/vertical direction diagonally up to +/- 215mm







Expansion in all three directions simultaneously



Material properties



excellent properties against ozone concentrations



very good long-term exposure very good flexibility at low heat resistance (up to + 120°C)



temperatures (down to - 40°C)



excellent properties against UV rays



excellent against water and water vapour



very good against alkalis, diluted acids and salt solutions



very good resistance to polar solvents such as alcohol and ketones

The EPDM material also has good general resistance to chemicals.

Resistance to non-polar plasticisers and solvents (e.g. mineral oils, petrol, fuels and aromatics such as toluene) is low. Constant contact with these media should be avoided.

Short-term contact during the installation phase with the open flame does not cause any impairment of the material properties.

| Test | Unit | Test standard | Test value |
|--|---------------------|-----------------------------|-------------------------|
| Hardness | Shore A | DIN 53505 | 40 ± 5 |
| Tensile strength | N / mm ² | DIN 53504 | > 10 |
| Elongation at break | % | DIN 53504 | > 700 |
| Compression set (at 23°C and 70°C) | % | DIN ISO 815-1 | 20% and 44% |
| respectively | | | |
| Resistance to ozone cracking | Crack level | DIN 53509-1 | Crack level 0 |
| Water vapour diffusion resistance | μ | DIN EN ISO 12572 | 83,000 μ |
| Fire behaviour | | DIN EN 13501-1 | Class E |
| | | | |
| Alkali resistance (storage in lime water) | | DIN EN 1847 | average > 5% |
| Alkali resistance (storage in lime water) Folding at low temperatures - 40°C | | DIN EN 1847 DIN EN 495-5 | average > 5 % No cracks |



Joints without weak points due to vulcanisation













Outside corner

Inside corner


Mitre


T-piece


Crosspiece


Inside corner 3-way

Other special fittings available.











Installation with change of direction







Installation details

Our service: Made to measure on site!












Installation















Made to measure



Rolls of 25 m from stock

Contact

Flexjoint GmbH

Mellingerstrasse 12 5443 Niederrohrdorf Switzerland

Office: +41 56 470 34 72 e-mail: info@flexjoint.ch

www.flexjoint.ch

Kaspar Hürlimann

Mobile: +41 79 795 53 99

